

Grade	Br				H <sub>cB</sub>		H <sub>cj</sub>		(BH) <sub>max</sub>			
	kGs		T		kOe	kA/m	kOe	kA/m	MGOe		kJ/m <sup>3</sup>	
	Max	Min	Max	Min	Min	Min	Min	Min	Max	Min	Max	Min
G50SH	14.4	13.9	14.4	13.9	13.0	1035	20	1592	50	47	398	374
G50SHT	14.4	13.9	14.4	13.9	13.0	1035	22	1751	50	47	398	374
G52SH	14.6	14.2	1.46	1.42	13.2	1050	20	1592	52	49	414	390
G52SHT	14.6	14.2	1.46	1.42	13.2	1050	22	1751	52	49	414	390
G45UH	13.7	13.2	1.37	1.32	12.4	987	23	2149	46	42	366	334
G45UHT	13.7	13.2	1.37	1.32	12.4	987	27	2149	46	42	366	334
G48UH	14.0	13.6	1.40	1.36	12.7	1011	25	1990	48	45	382	358
G48UHT	14.0	13.6	1.40	1.36	12.7	1011	27	2149	48	45	382	358
G50UH	14.4	13.9	14.4	13.9	13.0	1035	25	1970	50	47	398	374
G42EHT	13.3	12.8	1.33	1.28	12.0	955	32	2547	43	40	342	318
G45EH	13.7	13.2	1.37	1.32	12.4	987	30	2388	46	42	366	334
G45EHT	13.7	13.2	1.37	1.32	12.4	987	32	2547	46	42	366	334
G38AHT	12.6	12.1	1.26	1.21	11.8	939	37	2945	39	35	310	278
G40AH	12.9	12.5	1.29	1.25	12.0	955	35	2786	41	38	326	302
G40AHT	12.9	12.5	1.29	1.25	12.0	955	37	2945	41	38	326	302
G42AH	13.3	12.8	1.33	1.28	12.0	955	35	2786	43	40	342	318

Remark: 1. All the property test in room temperature 20°C~23°C.

2. All the "G" grade is by technical of grain boundary.